



Bitumen 10/20 Specifications:

No.	Analysis	Unit	Limit	Test Method
1	Density@25C	Kg/m3	1010-1060	ASTM D70 or D3289
2	Penetration@2cC	Mm/10	10-20	ASTM D5
3	Softening point	° C	° 120	ASTM D36
4	Ductility@25C	Cm	3 Min.	ASTM D113
5	Loss on heating	Wt%	0.2 Max	ASTM D6
6	Drop in penetration after heating	%	20 Max	ASTM D5 and D6
7	Flash point	° C	° 225 Min	ASTM D92
8	Solubility in Trichloroethylene	Wt%	99.0 Min	ASTM D4
9	Spot test		Negative	AASHTO T102
10	Viscosity@60vC			
11	Viscosity@135 C			
12	Wax conect			